


# TexWrite® 22

Cleanroom bond without organic fillers



## Description

TexWrite® 22 is a cleanroom bond paper impregnated with a synthetic copolymer to substantially reduce the risk of particle generation associated with standard papers. Unlike other cleanroom papers, TexWrite® 22 is formulated without organic fillers such as calcium carbonate, titanium dioxide or aluminum silicate. Although these fillers impart whiteness and opacity, they also contribute to ionic contamination. Eliminating organic fillers significantly reduces ionic contamination in the cleanroom.

TexWrite® 22 bond possesses both strength and excellent heat resistance, making it ideal for use in laser printers and photocopiers. TexWrite® 22 is available in white, blue, yellow, pink and green to allow for easy identification as cleanroom paper or to differentiate between shifts, areas or projects.

## Features

- No organic fillers
- No natural latex binders
- High strength and excellent heat resistance
- Excellent toner adhesion
- Cleanroom packaged
- Precision-cut edges

## Benefits

- Very low particle counts and sodium levels
- Reduced ionic and metal contamination
- Compatible with toner and offset printing
- Autoclavable for use in sterile environments

## Applications

- Standard-duty and high-speed laser printers and photocopiers
- No risk of latex associated reactions
- Offset printing
- Note taking, cleanroom manuals and work instructions



**North America**  
1210 South Park Drive  
Kernersville, NC 27284  
Tel (800) TEXWIPE  
(336) 996-7046  
Fax (336) 996-2297  
[www.texwipe.com](http://www.texwipe.com)  
[info@texwipe.com](mailto:info@texwipe.com)

**Europe/Middle East**  
Skejby Nordlandsvej 307  
DK-8200 Aarhus N  
Denmark  
Tel +45 87 400 220  
Fax +45 87 400 222

**Asia/Pacific**  
50 Tagore Lane  
#02-01 Entrepreneur Centre  
Singapore 787494  
Tel +65 6468 9433  
Fax +65 6468 6772

## Products

TX Number	Description	Packaging
<b>TX5812</b>	TexWrite® 22 Blue 8.5" x 11"	250 sheets/pack; 10 packs/box
<b>TX5815</b>	TexWrite® 22 White 8.5" x 11"	250 sheets/pack; 10 packs/box
<b>TX5814</b>	TexWrite® 22 Yellow 8.5" x 11"	250 sheets/pack; 10 packs/box
<b>TX5813</b>	TexWrite® 22 Pink 8.5" x 11"	250 sheets/pack; 10 packs/box
<b>TX5831</b>	TexWrite® 22 Green 8.5" x 11"	250 sheets/pack; 10 packs/box
<b>TX5816</b>	TexWrite® 22 Blue 8.5" x 11"; 3-hole punched	250 sheets/pack; 10 packs/box
<b>TX5916</b>	TexWrite® 22 White 8.5" x 11"; 3-hole punched	250 sheets/pack; 10 packs/box
<b>TX5909</b>	TexWrite® 22 Blue 9.5" x 11"; Continuous form	1500 sheets/box
<b>TX5820</b>	TexNotes TexWrite® 22; Blue 3" x 4" pads	72 sheets/pad; 10 pads/box
<b>A4 Paper</b>		
<b>TX5811</b>	TexWrite® 22 Blue A4	250 sheets/pack; 10 packs/box
<b>TX5819</b>	TexWrite® 22 White A4	250 sheets/pack; 10 packs/box
<b>TX5823</b>	TexWrite® 22 Pink A4	250 sheets/pack; 10 packs/box
<b>TX5824</b>	TexWrite® 22 Yellow A4	250 sheets/pack; 10 packs/box
<b>TX5829</b>	TexWrite® 22 Green A4	250 sheets/pack; 10 packs/box

# TexWrite® 22

TX5812 TX5815 TX5814 TX5813 TX5831  
 TX5816 TX5916 TX5909 TX5820 TX5811  
 TX5819 TX5823 TX5824 TX5829

## Performance Characteristics

Property	Typical Value	Test Method*
Basis weight	80 g/m <sup>2</sup>	TM2: The Determination of Basis Weight
Caliper	5.0 mil	
Tensile strength		
Machine direction	5.3 kg	Federal Standards No. 191A:Methods 5102
Cross direction	4.5 kg	Federal Standards No. 191A:Methods 5102
Tear strength		
Machine direction	78 g	Elmendorf tear test
Cross direction	79 g	
Opacity	74%	TAPPI Test Method T-425
Surface resistivity	2.6 x 10 <sup>9</sup> ohms** (2.6 x 10 <sup>10</sup> ohms/sq)	TM14: The Determination of Surface Resistivity of Fabrics and Other Thin, Flat Materials (Adapted from EOS/ESD-S11.11-1993)

## Contamination Characteristics

Property	Typical Value	Test Method*
Particles (>0.5 µm)	4.8 million particles/m <sup>2</sup>	TM5: Particles Released from Wipers and Other Materials Under Conditions of Minimal Stress
Ions		
Sodium	85 ppm	TM12: The Determination of Ions in Wipers and Other Materials by Capillary Ion Analysis (CIA) Technique
Chloride	50 ppm	TM12: The Determination of Ions in Wipers and Other Materials by Capillary Ion Analysis (CIA) Technique

**Note:** The data in this table represent typical analyses of these products. These are not specifications. ITW Texwipe continually refines both its processes and its products.

This data is the most accurate representation of the typical properties of these products at the time of publication.

\* ITW Texwipe test procedures available upon request.

\*\* TM14 at 55% RH.